




# HP Heavyweight Coated Paper



## The HP Designjet printing system—the complete solution

HP Designjet printers, Original HP inks and printheads, Original HP printing materials and HP Scitex printers, are designed to work together as a system to provide reliable, consistent results with every print.



## Accomplish more with consistent results

Roll or stack your time-sensitive documents right off the printer. Ideal for rich, color-accurate prints, working comps, and design proofs, this heavyweight, PEFC™-certified paper is easy to handle and provides high-quality, consistent results. From line drawings to illustrations and light ink-density graphics, see high-quality, consistent image quality print to print and roll to roll.

### Improve your response time

Handle prints with confidence right off the printer. An enhanced coating provides ink abrasion resistance to help you deliver on quick turnaround times.

### Do more, with the environment in mind

Gain versatility with this premium bright white paper. From working comps and design proofs to fine line drawings and illustrations, meet the project needs and the environmental objectives of your company and clients with a PEFC™-certified paper.

Target customers	Applications	Benefits
Architects	Posters and presentations	Rich, color-accurate prints and consistent, high-quality results
Engineers	POP and retail displays	Resistance to ink abrasion for easy handling
Geographic Information Systems (GIS) professionals	Geographic Information Systems (GIS)	100+ years display permanence indoor <sup>1</sup> ; in-window 3 months unlaminate <sup>2</sup> , 2 years laminate <sup>2</sup>
Graphic designers	Architecture (AEC) and engineering (MCAD)	PEFC™-certified paper
Print service providers		Recyclable through commonly available program

## Technical specifications



### HP Heavyweight Coated Paper

For the latest ICC/media profiles and a variety of resources to help you get the most out of your printer and HP large format printing materials, please visit [globalBMG.com/hp/](http://globalBMG.com/hp/).

<b>Weight</b>	130 g/m <sup>2</sup> per ISO 536 Test Method, (35 lbs)			
<b>Thickness</b>	167 microns/6.6 mil per ISO 534 Test Method			
<b>Opacity</b>	96% per TAPPI T-425 Test Method			
<b>Brightness</b>	89% per TAPPI T-452 Test Method			
<b>Whiteness</b>	144 per CIE Ganz 82 Test Method			
<b>Finish</b>	Matte			
<b>Operating temperature</b>	15 to 35° C / 59 to 95° F			
<b>Operating humidity</b>	20 to 80% RH			
<b>Display permanence (Indoor home or office)</b>	100+ years with Original HP 83 UV inks <sup>1</sup>			
<b>Display permanence (Commercial in-window)</b>	3 months unlamined, 2 years laminated with Original HP 91 Photo Inks <sup>2</sup>			
<b>Dry time</b>	Immediate (at 23° C, 50% RH)			
<b>Shelf life</b>	1 year, unopened in original packaging			
<b>Storage temperature</b>	0 to 40° C / 32 to 104° F			
<b>Storage humidity</b>	5 to 95% RH			
<b>Recyclability</b>	Recyclable through commonly available recycling programs			
<b>Country of origin</b>	Product of Germany			
<b>Ordering information</b>	<b>Product numbers</b>	<b>Roll sizes</b>	<b>UPC Codes</b>	<b>Region</b>
	C6029C <sup>3</sup>	610 mm x 30,5 m (24 in x 100 ft)	848412013108	North America, Europe, Asia
	C6030C <sup>3</sup>	914 mm x 30,5 m (36 in x 100 ft)	848412013115	Worldwide
	C6569C <sup>3</sup>	1067 mm x 30,5 m (42 in x 100 ft)	848412013122	Worldwide
	C6570C <sup>3</sup>	1372 mm x 30,5 m (54 in x 100 ft)	848412013146	North America, Europe, Asia
	C6977C <sup>3</sup>	1524 mm x 30,5 m (60 in x 100 ft)	848412013153	Worldwide
	Q1956A <sup>3</sup>	1067 mm x 67,5 m (42 in x 225 ft)	848412013139	North America, Europe
	Q1957A <sup>3</sup>	1524 mm x 67,5 m (60 in x 225 ft)	848412013160	North America, Europe

**Warranty** HP large format printing materials are free from defects in materials and workmanship. For warranty statement please see [globalBMG.com/hp/MediaWarranties](http://globalBMG.com/hp/MediaWarranties).

<sup>1</sup> With Original HP 83 UV inks. Display permanence rating for interior displays/away from direct sunlight, under glass by HP Image Permanence Lab and/or by Wilhelm Imaging Research, Inc. on a range of HP media. For more information, see [globalBMG.com/hp/t/printpermanence](http://globalBMG.com/hp/t/printpermanence).

<sup>2</sup> With Original HP 91 Photo Inks. Interior in-window display ratings by HP Image Permanence Lab on a range of HP media. HP predictions based on test data under Xenon-Arc illuminant—calculation assumes 6,000 Lux/12 hr day. For more information, see [globalBMG.com/hp/t/printpermanence](http://globalBMG.com/hp/t/printpermanence).



For detailed information on the HP large format print media portfolio and to order, visit [globalBMG.com/hp](http://globalBMG.com/hp)

